

Fibertherm universal dry 180

Beton  Wood

Thermal insulation in wood fiber panels with
180 kg/m³ density for roofs and walls

Specification



THERMAL INSULATION FOR NEW ROOFS OR RENOVATIONS

Supply and installation of the thermo-acoustic insulation of covering roofs with rigid wood fiber Fibertherm Universal dry panels arranged in a single layer and with tongue & groove interlocking edges that allow a better joint between the panels.

The external insulation of the covers must be protected with waterproofing.

The panels reduce the thermal bridges, they are realized in wood fiber with a density equal $\delta=180 \text{ Kg/m}^3$, produced with dry process according to the standards EN 13986 and EN 622-4 under constant quality control.

The material has the following thermodynamic characteristics: density approx. 180 kg/m^3 , declared thermal conductivity $\lambda=0,043 \text{ W/mK}$, resistance to vapor penetration coefficient $\mu=5$, specific heat capacity 2100 J/kgK , fire class E according to EN 13501-1, CE certified.

The dimensions of the panels correspond to ... mm for a thickness of ... mm.

The wood used in panel processing comes from forests controlled by reforestation cycles and complies with the FSC (Forest Stewardship Council®) guidelines.

For more informations about the uses and the installation,
our offices are ready to answer your questions on www.fibradilegno.com



COVERED EXTERNAL/INTERNAL INSULATION IN VERTICAL WALLS

Supply and installation of the external/internal thermo-acoustic insulation of vertical walls, in masonry or frame structural system, in false walls with one or more wood fiber FiberTherm universal dry panels substrates arranged in a single layer and with tongue & groove interlocking edges that allow a better joint between the panels.

The panels reduce the thermal bridges, they are realized in wood fiber with a density equal to $\delta=180 \text{ Kg/m}^3$, produced with dry process according to the standards EN 13986 and EN 622-4 under constant quality control.

The material has the following thermodynamic characteristics: density approx. 180 kg/m^3 , declared thermal conductivity $\lambda=0,043 \text{ W/mK}$, resistance to vapor penetration coefficient $\mu=5$, specific heat capacity 2100 J/kgK , fire class E according to EN 13501-1, CE certified.

The dimensions of the panels correspond to ... mm for a thickness of ... mm.

The wood used in panel processing comes from forests controlled by reforestation cycles and complies with the FSC (Forest Stewardship Council®) guidelines.

Head office:
Via Falcone e Borsellino, 58
I-50013 Campi Bisenzio (FI)

T: +39 055 8953144
F: +39 055 4640609

info@betonwood.com
www.betonwood.com

FTHUD IR.18.02



Das Zeichen für verantwortungsvolle Waldbirtschaft

